

GENERAL FEATURES

- True Deep cycle construction
- Thick plate with high Tin low Calcium alloy
- High Reliability and Good Quality
- Deep Discharge Recovery
- High Power Density
- Long float and cyclic service life




APPLICATIONS

- Golf/Utility Vehicles
- Floor Machines
- Aerial Work Platform
- Recreational Vehicles(RV)
- Medical Mobility/Marine Vessels
- Neighborhood Electric Vehicles(NEV)
- Renewable Energy Systems



DIMENSIONS & WEIGHT

Length(mm)	295±1
Width(mm)	178±1
Height(mm)	346±1
Total Height(mm)	365±1
Weight(kg)	55.3±3%



COMPLIED STANDARDS

IEC 60896-21/22	JIS C8704
YD/T799	BS6290 part4
GB/T 19638	UL 1989

TECHNICAL SPECIFICATIONS



Nominal Voltage		6V(3 cells per unit)
Design Floating Life @25°C		12 Years
Nominal Capacity @25°C(20 hour rate@19.00A,10.50V)		380Ah
Capacity @25°C	10 hour rate (34.58A,10.8V)	345.8Ah
	5 hour rate (60.40A,10.5V)	302.0Ah
	1 hour rate (211.3A,9.6V)	211.3Ah
Internal Resistance	Full Charged Battery@25°C	≤2.0mΩ
Ambient Temperature	Discharge	-20°C~50°C
	Charge	-20°C~50°C
	Storage	-20°C~50°C
Max.Discharge Current@25°C		2000A(5s)
Capacity affected by Temperature (10 hr Capacity)	40°C	102%
	25°C	100%
	0°C	85%
	-15°C	65%
Self-Discharge@25°C per Month		3%
Charge (Constant Voltage) @25°C	Standby Use	Initial Charging Current Less than 68.4A Voltage 6.8-6.9V
	Cycle Use	Initial Charging Current Less than 68.4A Voltage 7.2-7.45V

BATTERY DISCHARGE TABLE

Discharge Constant Current per Cell (Amperes at 25°C)







F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h	100h
1.60V	489.1	312.4	229.5	211.3	134.1	94.2	63.8	42.2	37.62	20.14	4.56
1.67V	480.3	306.7	225.3	207.1	131.5	92.3	62.7	41.4	36.86	19.76	4.48
1.70V	471.2	301.0	221.2	203.3	129.2	90.8	61.6	40.7	36.10	19.38	4.37
1.75V	462.5	295.3	217.0	199.5	126.5	88.9	60.4	39.9	35.72	19.00	4.29
1.80V	444.6	283.9	208.6	191.9	121.6	85.5	58.1	38.4	34.58	18.81	4.22

Discharge Constant Power per Cell (Watts at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	8h	10h	20h	100h
1.60V	941.3	601.2	441.9	405.5	257.6	180.9	123.1	80.9	72.6	39.3	8.78
1.67V	924.2	590.1	433.6	398.2	253.1	177.8	120.8	79.8	71.1	38.5	8.59
1.70V	907.1	579.1	425.6	390.6	248.5	174.4	118.6	78.3	69.9	38.2	8.44
1.75V	890.0	568.1	417.6	383.4	243.6	171.0	116.3	76.8	68.4	37.6	8.28
1.80V	855.8	546.4	401.7	368.6	234.5	164.5	112.1	73.7	65.7	36.5	8.13

Note The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Contact **CBB** for the latest information.

PERFORMANCE CHARACTERISTICS



BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container & Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	ABS (UL94-V0 optional)	Flame Si-Rubbeand aging resistancer	Female Copper Insert DT(torque:1 0~12N.m)	Advanced AGM separator for high pressure cell design	Dilute high purity sulphuric acid	Two layers epoxy resin seal

CBB Battery Technology Co.,Ltd.

RM504,55 Hanxing Zhong Road,Zhongcun, Panyu,Guangzhou 511495 China
Tel: +86-020-84888946 Fax: +86-020-62824569

Koyama®

www.cbb-battery.com