

### GENERAL FEATURES

- Environmentally friendly
- Can be used at vertical or horizontal orientation
- High Reliability and Good Quality
- High gas recombination efficiency
- High Power Density
- Maintenance-Free Operation



### APPLICATIONS

- UPS & EPS
- Emergency lighting Systems
- Medical Equipment
- Cable TV Systems
- Alarm Systems
- Electric Test Equipment
- Security Systems



### DIMENSIONS & WEIGHT

Length(mm)	260±1
Width(mm)	169±1
Height(mm)	211±1
Total Height(mm)	215±1
Weight(kg)	22.0±3%



### COMPLIED STANDARDS

IEC 60896-21/22	JIS C8704
YD/T799	BS6290 part4
GB/T 19638	UL 1989

### TECHNICAL SPECIFICATIONS



Nominal Voltage		12V(6 cells per unit)
Design Floating Life @25°C		10 Years
Nominal Capacity @25°C(10 hour rate@7.50A,10.80V)		75Ah
Capacity @25°C	20 hour rate (4.01A,10.5V)	80.2Ah
	5 hour rate (13.2A,10.5V)	66.0Ah
	1 hour rate (47.9A,9.6V)	47.9Ah
Internal Resistance	Full Charged Battery@25°C	≤6.5mΩ
Ambient Temperature	Discharge	-20°C~50°C
	Charge	-20°C~50°C
	Storage	-20°C~50°C
Max.Discharge Current@25°C		750A(5s)
Capacity affected by Temperature (10 hr Capacity )	40°C	102%
	25°C	100%
	0°C	85%
	-15°C	65%
Self-Discharge@25°C per Month		3%
Charge (Constant Voltage) @25°C	Standby Use	Initial Charging Current Less than 18.75A Voltage 13.6-13.8V
	Cycle Use	Initial Charging Current Less than 18.75A Voltage 14.4-14.9V

### BATTERY DISCHARGE TABEL

#### Discharge Constant Current per Cell (Amperes at 25°C)







F.V/Time	15min	30min	45min	1h	2h	3h	5h	6h	8h	10h	20h
1.60V	135.4	79.7	60.4	47.9	28.1	20.7	14.0	12.2	9.5	7.9	4.16
1.67V	127.9	75.5	58.1	46.4	27.2	20.0	13.7	11.9	9.5	7.7	4.13
1.70V	120.1	73.4	56.0	44.6	26.5	19.5	13.4	11.7	9.3	7.7	4.07
1.75V	112.5	70.1	53.5	42.8	25.8	19.1	13.2	11.5	9.2	7.6	4.01
1.80V	105.5	67.6	51.5	41.3	24.8	18.5	12.9	11.3	9.0	7.5	3.98

#### Discharge Constant Power per Cell (Watts at 25°C)

F.V/Time	15min	30min	45min	1h	2h	3h	5h	6h	8h	10h	20h
1.60V	258.8	158.3	114.7	91.8	53.3	39.5	26.9	23.5	18.6	15.4	8.2
1.67V	247.7	148.4	110.8	89.3	51.9	38.5	26.5	23.1	18.5	15.2	8.2
1.70V	230.8	145.2	107.3	86.3	50.7	37.6	26.1	22.8	18.2	15.1	8.1
1.75V	216.5	138.2	103.0	83.1	49.5	36.8	25.7	22.4	18.0	14.9	8.0
1.80V	203.3	132.6	99.5	80.4	47.9	35.8	25.2	22.1	17.8	14.9	7.9

**Note** The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Contact **CBB** for the latest information.

### PERFORMANCE CHARACTERISTICS



### BATTERY CONSTRUCTION

Component	Positive plate	Negative plate	Container & Cover	Safety valve	Terminal	Separator	Electrolyte	Pillar seal
Features	Thick high Sn low Ca grid with special paste	Balanced Pb-Ca grid for improved recombination efficiency	ABS (UL94-V0 optional)	Flame Si-Rubber and aging resister	Female Copper Insert M6 (torque: 4~6N.m)	Advanced AGM separator for high pressure cell design	Dilute high purity sulphuric acid	Two layers epoxy resin seal

**CBB Battery Technology Co., Ltd.**

RM504,55 Hanxing Zhong Road, Zhongcun, Panyu, Guangzhou 511495 China  
 Tel: +86-020-84888946 Fax: +86-020-62824569

# Koyama®

www.cbb-battery.com